



+++++ TECHNICAL DATA SHEET

EMPEYOL F6522/2F6522

DESCRIPTION

EMPEYOL F6522 / 2F6522 is a 6000 molecular weight trihydroxy polyether polyol containing a high percentage of primary hydroxyl groups. It is used in several urethane applications - most notably in high resilience moulded foams and also in semi - flexible foams and other urethane systems.

SALES SPECIFICATION

S. NO	CHARACTERISTICS	UNIT	SPECIFICATION
1	Appearance	----	Clear viscous liquid
2	Density at 25° C	grams/cc	1.015 - 1.025
3	Viscosity at 25° C	cps	1100 (Maximum)
4	Hydroxyl Number	mg KOH / g	26.0 - 28.0
5	Water	% w/w	0.10 (maximum)

PACKING SIZE: 210 kg nett.

STORAGE AND HANDLING

EMPEYOL F6522 / 2F6522 polyol is to be stored in tightly closed containers preferably at temperatures between 20 - 35 °C.

Should wear gloves and goggles during handling.

SHELF LIFE: 1 YEAR

HEALTH AND SAFETY ADVICE

EMPEYOL F6522 / 2F6522 polyol should present no unusual health problems when used in manufacturing operations where satisfactory standards of personal and industrial hygiene are maintained. Precautions should be taken to avoid exposure to the eye or prolonged contact with the skin.

Warning : The information in this data sheet is believed to be accurate but all recommendations are made without warranty, since the conditions of use are beyond the company's control. MPL disclaims any liability in connection with the use of the information, and does not warrant against infringement by reason of the use of any of its products in combination with other materials or in any process.

Revision No. 3

Date of issue: JANUARY 2011