



## \*\*\*\*\* TECHNICAL DATA SHEET

### EMPEYOL F4922

#### PRODUCT DESCRIPTION :

**EMPEYOL F4922** is a 4900 molecular weight, trihydroxy polyether polyol containing a high percentage of primary hydroxyl groups. It is used in several urethane applications - most notably in high resilience moulded foams and also in semi-flexible foams and RIM elastomers.

#### SALES SPECIFICATION :

S.NO	CHARACTERISTICS	UNIT	SPECIFICATION
1	Appearance	----	Clear viscous liquid
2	Density at 25° C	g/cc	1.015 - 1.025
3	Viscosity at 25° C	cps	850 maximum
4	Water	% w/w	0.10 maximum
5	Hydroxyl Number	mgKOH/g	34.0 - 36.0

#### PACKING SIZE

210 kg Nett / 25 kg Nett

#### HANDLING & STORAGE :

EMPEYOL F4922 polyol is to be stored in tightly closed containers preferably at temperatures between 20 - 35° C. Should wear gloves and goggles during handling.

#### SHELF LIFE : 1 YEAR

#### HEALTH & SAFETY ADVICE :

EMPEYOL F4922 polyol should present no unusual health problems when used in manufacturing operations where satisfactory standards of personal and industrial hygiene are maintained. Precautions should be taken to avoid exposure to the eye or prolonged contact with skin.

**Warning :** This information is believed to be accurate but all recommendations are made without warranty, since the conditions are beyond the company's control. MPL disclaims any liability in connection with the use of information, and does not warrant against infringement by reason of the use of any of its products in combination with other materials or in any process.

Revision No. : 2

Date of issue : January 2011