

Product Name

 Date of issue: Sep. 2020
 Revision No : 0

EMPEYOL WSF 300/3 (MIDSOLE)

Product Description

EMPEYOL WSF 300/3 is an eco-friendly formulated polyether polyol to be used in combination with suitable isocyanate for the production of microcellular polyurethane elastomers for Midsole inbetween EVA/RUBBER application.

Properties of Polyol

Characteristics	Unit	Specification
Appearance	-	White to Pale yellow liquid
Viscosity @25°C	cps	1000 ± 100
Density @25°C	g/cc	1.020 ± 0.020

Recommended Process Conditions in Bench Mixer at 25°C

Process Parameters	Unit	Specification
Mixing ratio (Polyol : Isocyanate)	-	100 : (60-70)
Polyol Temperature	°C	25 ± 02
MDI Temperature	°C	25 ± 02
Cream time	sec	16+2
Gel time	sec	28+2
Tack free time	sec	37+5
Pinch Time	Sec	70-75
Free rise density	Kg/m ³	250 ± 20
Demold time	sec	210

Properties of Foam

Properties	Test Method	Unit	Specification
Molded Density		Kg/m ³	400 ± 20
Shore A	SATRA TM 205:2017	No unit	20-25

The information in this data sheet is believed to be accurate but all recommendations are made without warranty since the conditions of use are beyond the company's control. MPL disclaims any liability in connection with use of the information and does not warrant against infringement by reason of the use of any of its products in combination with other materials or in any process.



TECHNICAL DATA SHEET

Manali Petrochemicals Limited.,
Ponneri High Road, Manali,
Chennai -600 068
Ph: 25941557/3910/1025
Fax: 25941199

Packaging Size

200 kg

Shelf-Life

6 Months

**Storage and
Handling**

EMPEYOL WSF 300/3 and Empeyonate ISE MPP205 should be stored in tightly closed containers at temperature between 20°C and 30°C and should not be exposed to direct sunlight.

**Health and
Safety Advice**

EMPEYOL WSF 300/3 polyol should present no unusual health problems when used in manufacturing operations where satisfactory standards of personal and industrial hygiene are maintained. Precautions should be taken to avoid exposure to the eye or prolonged contact with the skin.

The information in this data sheet is believed to be accurate but all recommendations are made without warranty since the conditions of use are beyond the company's control. MPL disclaims any liability in connection with use of the information and does not warrant against infringement by reason of the use of any of its products in combination with other materials or in any process.

Regd. Office: "SPIC House" 88, Mount Road, Guindy, Chennai – 600032
Visit us at: www.manalipetro.com

CIN : L2429TN1986PLC013087 email ID : mkt@manalipetro.com

Page No.2